

# LINGERIE

Luxury & Technology

by SITIP

*Subbie*

155 cm - 80 g/m<sup>2</sup>  
82% PA - 18% EA



C 186  
CONFETTO

C 034  
ALBA

C 118  
PRIMAVERA

M 226  
TEMPEST

C 168  
NINFEA

C 056  
PERLA

M 136  
ROMANTIC TEA

M 116  
ZENZERO

S 279  
AVOCADO

S 281  
MALVA

S 529  
MIDNIGHT

37  
CAMINO

S 368  
PINK VELVET

M 137  
PEONIA

S 280  
FELCE

X 029  
MAYA

S 496  
MALTESE

X 60  
NERO

560  
BIANCO

03  
PANNA

C 506  
SKINNY

C 507  
PATCHOULY





Colore / Colour	N°	Luce Light UNI EN ISO 105 B02		Sfregamento Crocking Secco Dry Umido Wet UNI EN ISO 105 X12		Lavaggio 40°C - A1S Washing 40°C - A1S UNI EN ISO 105 C06		Acqua Severa Water Staining UNI EN ISO 105 E01		Sudore Acido Perspiration Acid UNI EN ISO 105 E04		Sudore Basico Perspiration Alkaline UNI EN ISO 105 E04	
		C.C.	S.CO	S.CO	S.PA	S.CO	S.PA	S.CO	S.PA	S.CO	S.PA	S.CO	
ALBA	C 034	5	5	5	5	5	5	4/5	4/5	4/5	4/5	4/5	4/5
AVOCADO	S 279	> 5	4/5	4/5	4/5	4/5	4/5	4	4/5	4/5	4/5	4	4/5
BIANCO	560	3/4	5	5	5	5	5	5	5	5	5	5	5
CAMINO	37	> 5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
CONFETTO	C 186	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
FELCE	S 280	5	4/5	4/5	3/4	4	3/4	4	4	4	4	3/4	4
MALTESE	S 496	5	4/5	4/5	4/5	4/5	4	4	4	4	4	4	4
MAYA	X 029	> 5	5	5	4	4	3	3/4	3/4	4	3/4	4	4
MALVA	S 281	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
MIDNIGHT	S 529	5	4/5	4/5	4/5	4/5	4	4	4	4	4	4	4
NERO	X 60	> 5	4/5	4/5	3/4	4	3/4	4	3/4	4	3/4	4	4
NINFEA	C 168	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
PANNA	03	> 5	5	5	5	5	5	5	5	5	5	5	5
PATCHOULY	C 507	> 5	5	5	5	5	4/5	5	4/5	5	4/5	5	5
PEONIA	M 137	4/5	4/5	4/5	4/5	4/5	4	4/5	4/5	4/5	4/5	4	4/5
PERLA	C 056	5	5	5	5	5	4/5	4/5	4/5	5	4/5	4/5	4/5
PINK VELVET	S 368	3/4	4/5	4/5	4	4/5	4	4/5	4	4/5	4	4/5	4/5
PRIMAVERA	C 118	> 5	4/5	4/5	4/5	4/5	4	4/5	4	4/5	4	4/5	4/5
ROMANTIC TEA	M 136	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
SKINNY	C 506	> 5	5	5	5	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
TEMPEST	M 226	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
ZENZERO	M 116	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5

Luce Light	Valutazioni Assessments	Altri Test Other Tests	Valutazioni Assessments
---------------	----------------------------	---------------------------	----------------------------

1	debolissima very weak	1	debole weak
2	debole weak	2	scarsa limited
3	moderata moderate	3	abbastanza buona fair
4	abbastanza buona fair	4	buona good
5	buona good	5	ottima excellent
6	buonissima very good	* Colori Fluorescenti / * Fluo Colors	
7	ottima excellent	C.C. = Cambio Colore / Colour discoloration	
8	eccezionale exceptional	S.CO = Stingimento su Cotone / Staining on Cotton	
		S.PA = Stingimento su Poliammide / Staining on Polyamide	

Raccomandiamo la massima attenzione nella lettura dei valori di solidità. Sconsigliamo abbinamenti/intarsi tra colori che abbiano valori di solidità a lavaggio, acqua o acqua di mare inferiori a 4. In caso di necessità di abbinamento/intarsio consigliamo sempre una prova preventiva.

*Please pay special attention to the fastness values declared on the colour card. Combination of colours is not recommended when the fastness values of washing, water or sea water are lower than 4. In case of combination we suggest a trial before.*



Headquarters  
**SITIP S.p.A.** Via Vall'Alta, 13 - 24020 Cene (BG) Italy - Tel. +39 035 736511 - Fax +39 035 719003 - info@sitip.it  
www.sitip.it